

●Amber factice

| Name     | Acetone<br>extract<br>[%] | Free<br>sulfur<br>[%] | Ash<br>[%] | Specific<br>gravity<br>at 20°C | Appearance     | Net wt.<br>[kgs] |
|----------|---------------------------|-----------------------|------------|--------------------------------|----------------|------------------|
| Amber    | 17~23                     | ≤0.1                  | ≤1.5       | 1.04                           | Amber<br>block | 25               |
| Amber L  | 27~33                     | ≤0.1                  | ≤1.5       | 1.01                           |                |                  |
| Amber#50 | 40~48                     | ≤0.1                  | ≤1.5       | 0.99                           |                |                  |

○Applications

NR

SBR・NBR・EPDM etc.

○Uses

white or light colored and transparent products, rubber bands and other industrial articles

- ・Amber factice is a little softer than white factice, and is packed in plate form.
- ・It contains small quantity of magnesium oxide as stabilizer.
- ・"Amber L" and "Amber#50" contain naphthenic mineral oils.
- ・It causes the delay of vulcanizing same as white factice and the same actions are needed.